

<b>STANDARD MEDIA</b>	<b>MAX TEMP</b>	<b>DESCRIPTION</b>
<b>Natural Cotton</b>	300 F	For organic solvents, water, dilute acids, oils, paints and alcohols and other chemicals.
<b>Bleached Cotton</b>	300 F	Used for the same applications as natural cotton and also for potable liquids, vegetable oils and beverages, FDA material.
<b>Rayon</b>	300 F	Chemical Compatibility similar to cotton. Used primarily in filtration of petroleum oils.
<b>Polypropylene</b>	200 F	Best overall media for water and corrosive fluids and low temperature applications.
<b>FDA Polypropylene</b>	200 F	Same compatibility as polypropylene, permits contact with food and edible products, FDA material.
<b>Fibrilated Polypropylene</b>	150 F	No additives or finishes, used in ultra-pure liquids, less dirt holding capacity than other polypropylenes, FDA material.
<b>Polyester</b>	300 F	Chemical compatibility similar to polypropylene with higher temperature rating.
<b>Nylon</b>	325 F	For concentrated alkalis and solvents.
<b>Fiberglass</b>	400/750 F	Filtration of organic acids, organic solvents, petroleum oils, mineral acids, and other corrosive and high temperature applications.
<b>CORE</b>	<b>MAX TEMP</b>	<b>CHARACTERISTICS</b>
<b>Tinned Steel</b>	400 F	General purpose metal core for oils, solvents, paints and non-FDA applications.
<b>Polypropylene</b>	200 F	Best all around material for lower temperature applications of water and corrosive fluids. Easily incinerated, FDA material.
<b>Polyester</b>	350F	Similar to Polypropylene with higher temp rating, FDA material.
<b>304 Stainless Steel</b>	750 F	Corrosion resistant, FDA material.
<b>316 Stainless Steel</b>	750F	More corrosion resistant, FDA material.